

# A solid electrolyte hydrogen sensor with an electrochemically-supplied hydrogen standard

Koji Katahira<sup>a,\*</sup>, Hiroshige Matsumoto<sup>a</sup>, Hiroyasu Iwahara<sup>a</sup>,  
Kunihiro Koide<sup>a</sup>, Takashi Iwamoto<sup>b</sup>

<sup>a</sup>Center for Integrated Research in Science and Engineering, Nagoya University, Furo-cho, Chikusa-ku, Nagoya 464-8603, Japan

<sup>b</sup>TYK Corporation, Advanced Materials Research and Development Center, 3-1 Ohbata-cho, Tajimi, Gifu 507-8607, Japan

Received 11 September 2000; received in revised form 4 October 2000; accepted 16 October 2000

## Abstract

A high-temperature solid electrolyte hydrogen sensor consisting of two electrochemical cells was investigated. One cell was employed for electrochemical pumping of hydrogen from hydrogen-containing atmosphere and the other was used for sensing of the ambient hydrogen with the pumped hydrogen as a standard gas. On applying a voltage above 2.5 V to the pumping cell, a sufficient EMF response against hydrogen partial pressure was observed over a wide range of  $P_{H_2}$ . The required voltage of the pumping cell was affected by the hydrogen partial pressure in the test gas. © 2001 Elsevier Science B.V. All rights reserved.

**Keywords:** Hydrogen sensor; Proton-conducting ceramics; Hydrogen pump; Hydrogen concentration cell

## 1. Introduction

SrCeO<sub>3</sub>- and CaZrO<sub>3</sub>-based oxides exhibit appreciable proton conduction under hydrogen-containing atmosphere at high temperatures [1–3]. Using these oxides as a solid electrolyte, high-temperature-type hydrogen sensor can be constructed [4,5]. A hydrogen sensor for molten metals has been developed and widely used in the process control in the metal melting industry [6,7]. However, the hydrogen sensor needs a standard gas with a known hydrogen pressure, e.g. 1% hydrogen argon-balanced gas, and thus the sensor system needs to equip the gas cylinder [6]. If such external standard material is excluded, it is possible to miniaturize the sensor device. Although molecular sieve, AlPO<sub>4</sub>·xH<sub>2</sub>O, etc. were examined as internal solid standard materials [5], long-time stability and reproducibility were still insufficient for a practical use. Hydrogen sensors based on the change in electrical conductivity of high-temperature-type protonic conductor have been studied [8–10].

Different from conductivity-type sensor, we have proposed a new-type steam sensor using two electrochemical cells [11]. One cell was employed for electrochemical pumping of hydrogen by means of electrolysis of water vapor in the atmosphere. Water vapor pressure could be determined from EMF of the other cell using the pumped

hydrogen as a standard gas. In this paper, this working principle was applied to hydrogen sensor and the sensing performance was investigated.


## 2. Working principle of the hydrogen sensor

The working principle of the present hydrogen sensor is fundamentally the same as that in our previous paper of a steam sensor [11]. This principle of the hydrogen sensor is schematically illustrated in Fig. 1. The sensor consists of two proton-conducting electrolytes and a semi-closed gas compartment between the electrolytes. A constant voltage is applied to one cell to pump up hydrogen from a hydrogen-containing gas to be measured by the following electrode reactions.

Outer electrode of pumping cell < anode >



Inner electrode of pumping cell < cathode >



The hydrogen gas thus pumped was accumulated in a compartment between the pumping cell and the sensing cell. A small leakage is provided for the standard gas compartment, so that the hydrogen pressure in the compartment can be kept equal to the atmospheric pressure

\* Corresponding author. Tel.: +81-572-25-7181; fax: +81-572-24-7181.

Fig. 2. EMF response of the sensing cell and the voltage-current relation of pumping cell at 700°C.




Fig. 3. EMF response of the sensing cell and applied to the pumping cell as a parameter of hydrogen partial pressure in the test gas (700°C).

voltage higher than 1.0 V was applied. This result suggests that the partial pressure of hydrogen in the standard gas compartment increased with the voltage and became constant when a sufficient voltage was applied to the pumping cell. Such dependence of EMF on the applied voltage was similar to that observed for the steam sensor previously reported by the authors [11].

Fig. 3 shows the relation between the EMFs of the sensing cell and the applied voltage of the pumping cell under various hydrogen partial pressures. All the EMFs increased with increasing applied voltage and became unchanged after certain voltages were applied. The values of applied voltage necessary to obtain constant EMF increased with partial pressure of hydrogen in the test gas.

EMF of the sensing cell with pumping voltages 2.0–3.0 V is plotted against logarithm of hydrogen partial pressure of the test gas in Fig. 4. Dashed line shows the theoretical EMF calculated from Eq. (4); the hydrogen pressure in the standard gas compartment is assumed to be 1 atm. The relation between the observed EMF and  $P_{H_2}$  was in good




Fig. 4. EMF response of the sensor to hydrogen partial pressure in the test gas (700°C).

agreement with theoretical one when a voltage higher than 2.5 V was applied. This result indicates that the small open hole provided for the standard gas compartment is filled with hydrogen at 1 atm upon pumping a sufficient amount of hydrogen. The present hydrogen sensor, thus, worked in accordance with the presumed working principle described in Section 2, and could determine the partial pressures of hydrogen in the range from 1 to, at least, 0.01 atm.

#### 4.2. The response speed of the sensor

EMF response was examined by changing hydrogen partial pressures in the test gas. Fig. 5 shows the time evolution of the EMF for test gases with  $P_{H_2}$  in the range of 0.011–1.0 atm; applied voltage for the pumping cell was 2.5 V. The EMF exhibited quick response against the changes in hydrogen partial pressures and indicated stable values. The time required to reach 90% of the final value was about 100 s. All the EMF values were close to the theoretical ones. When the circuit of the pumping cell was opened, the EMF of the sensing cell decreased slowly to 0 mV. This result indicates that the pumped hydrogen from the test gas flows away through the small hole and inversely the test gas with low content of hydrogen comes into the hole.

An initial response of the sensor was tested under a constant atmosphere of  $P_{H_2} = 0.011$  atm in the test gas, and the result is shown in Fig. 6. Before applying the voltage to the pumping cell of the hydrogen sensor, a small uncertain EMF was observed which might be affected by a former measurement; as shown Fig. 5, it takes a long time to obtain the same atmosphere for the standard gas compartment and a test gas. However, on applying a voltage to the pumping cell, the EMF increased quickly and reached a theoretical value in 20 s.

In any cases, the response speed is very quick and it is sufficient for a practical use. This sensing performance depends on the size of the sensor cell, particularly, on the size of open hole of the pumping cell. Therefore, in the




Fig. 5. EMF response of the hydrogen sensor at 700°C.




Fig. 6. EMF response of the hydrogen sensor at 700°C.

future, it would be able to miniaturize sensor device and facilitate the handling.

#### 4.3. Required voltages for the pumping cell

From the discussion in Section 4.2, it has become clear that this hydrogen sensor can be utilized for a practical use. However, applied voltages were relatively large. In order to clarify this reason, the relation between the current density and the applied voltage of the pumping cell was plotted in Fig. 7. Under low hydrogen partial pressure the current densities do not increase in the range of low applied voltage. This phenomenon suggests that hydrogen was hardly pumped in this applied voltage range. This reason is probably the concentration polarization of hydrogen [12]. Thus the large applied voltage was needed to detect hydrogen gas in low concentration.

To understand this phenomenon, the plot of the EMFs of the sensing cell against current density of the pumping cell was shown in Fig. 8. EMFs increased with increasing current density and they reached a constant value at almost the same




Fig. 7. Relation between current density and applied voltage of pumping cell at 700°C.




Fig. 8. Relation between EMF of sensing cell and current density of the pumping cell at 700°C.

current density despite the difference in hydrogen partial pressure. This result suggests that a certain current density is needed in maintaining the hydrogen partial pressure in the standard gas compartment. The applied voltage to obtain sufficient current density is different for a given hydrogen partial pressure in the test gas. Because of the concentration polarization of hydrogen at the anode of pumping cell and because of relatively large size of the hole, the large applied voltage needs to detect hydrogen in a low partial pressure in the test gas.

#### 5. Conclusion

A high-temperature solid electrolyte hydrogen sensor using two electrochemical cells was investigated. On applying a voltage above 2.5 V to the pumping cell, the EMF of sensing cell reached the theoretical value for the hydrogen partial pressure of the test gas. The response speed of the sensor was very fast and would be sufficient for a practical use. A certain current density is needed for maintaining the hydrogen partial pressure of the standard gas compartment. The applied voltage to obtain sufficient current density is different for the hydrogen partial pressure in the test gas. Because of the concentration polarization of hydrogen and the size of the sensor cell, relatively large applied voltage is needed to detect low partial pressure of hydrogen in the test gas.

#### References

- [1] H. Iwahara, T. Esaka, H. Uchida, N. Maeda, Proton conduction in sintered oxides and its application to steam electrolysis for hydrogen production, *Solid State Ionics* 3/4 (1981) 359.
- [2] H. Iwahara, H. Uchida, K. Ono, K. Ogaki, Proton conduction in sintered oxides based on  $\text{BaCeO}_3$ , *J. Electrochem. Soc.* 135 (1988) 529.
- [3] T. Yajima, H. Kazeoka, T. Yogo, H. Iwahara, Proton conduction in sintered oxides based on  $\text{CaZrO}_3$ , *Solid State Ionics* 47 (1991) 271.

- [4] H. Iwahara, H. Uchida, K. Ogaki, H. Nagato, Nernstian hydrogen sensor using BaCeO<sub>3</sub>-based, proton-conducting ceramics operative at 200–900°C, *J. Electrochem. Soc.* 138 (1991) 295.
- [5] T. Yajima, H. Iwahara, K. Koide, K. Yamamoto, CaZrO<sub>3</sub>-type hydrogen and steam sensors: trial fabrication and their characteristics, *Sens. Actuator B* 5 (1991) 145.
- [6] T. Yajima, K. Koide, H. Takai, N. Fukatsu, H. Iwahara, Application of hydrogen sensor using proton conductive ceramics as a solid electrolyte to aluminum casting industries, *Solid State Ionics* 79 (1995) 333.
- [7] N. Fukatsu, N. Kurita, K. Koide, T. Ohashi, Hydrogen sensor for molten metals usable up to 1500 K, *Solid State Ionics* 113–115 (1998) 219.
- [8] N. Kurita, N. Fukatsu, T. Ohashi, Hydrogen analyzer based on coulometric titration using proton conductive solid electrolyte, *J. Jpn. Inst. Metals* 58 (1994) 782.
- [9] I. Kosacki, H.U. Anderson, Nanostructured oxide thin films for gas sensors, *Sens. Actuator B* 48 (1998) 263.
- [10] T. Inaba, K. Saji, H. Takahashi, Limiting current-type gas sensor using a high temperature-type proton conductor thin film, *Electrochemistry* 67 (1999) 458.
- [11] K. Katahira, H. Matsumoto, H. Iwahara, K. Koide, T. Iwamoto, Solid electrolyte steam sensor with an electrochemically-supplied hydrogen standard, *Sens. Actuator B* 67 (2000) 189.
- [12] H. Matsumoto, Y. Iida, H. Iwahara, Current efficiency of electrochemical hydrogen pumping using a high-temperature proton conductor SrCe<sub>0.95</sub>Yb<sub>0.05</sub>O<sub>3- $\lambda$</sub> , *Solid State Ionics* 127 (2000) 345.